


AMENDMENTS TO THE CLAIMS

1. **(Currently amended)** A moisture-curable polyurethane hot-melt adhesive, which comprises urethane prepolymer obtained by a reaction between polyisocyanate and polyols, wherein the polyols comprise:

long-chain aliphatic polyester polyol (A) represented by a general formula (I); aliphatic polyether polyol (B) having a number average molecular weight of 3,000 to 15,000; ~~and~~ aromatic polyester polyol (C1) which has a number average molecular weight of 1,000 to 5,000 and has a glass-transition temperature of 40°C or more, and aromatic polyester polyol (CII) which has a number average molecular weight of 400 to 3,500, a glass-transition temperature of 20°C or less, wherein said aromatic polyester polyol (CII) is obtained by a reaction between a polyol having a low molecular weight and a side chain(s), and o-phthalic acid,



wherein R¹ and R² each independently represents a straight chain alkylene group wherein the number of carbon atoms in the group is an even number, the sum of the number of carbon atoms in R¹ and R² is 12 or more, and n represents a number of 3 to 40.

2. **(Canceled)**

3. **(Original)** The moisture-curable polyurethane hot-melt adhesive according to claim 1, wherein the aliphatic polyetherpolyol (B) is a polypropylene glycol or polybutylene glycol, which has a number average molecular weight of 3,000 to 15,000.

4. **(Original)** The moisture-curable polyurethane hot-melt adhesive according to claim 1, wherein the aliphatic polyetherpolyol (B) is ethylene oxide denatured polypropylene glycol or

ethylene oxide denatured polybutylene glycol, which is obtained by adding ethylene oxide to both terminal ends of polypropylene glycol or polybutylene glycol.

5. (Previously Presented) The moisture-curable polyurethane hot-melt adhesive according to claim 4, wherein the aliphatic polyetherpolyol (B) comprises 20% by mass or less of structural units originating from ethylene oxide based on the total amount of the aliphatic polyetherpolyol (B).

6. (Previously Presented) The moisture-curable polyurethane hot-melt adhesive according to claim 1, wherein the adhesive is obtained by a reaction of the polyisocyanate and the polyols, which comprises 20 to 60 parts by mass of the long-chain aliphatic polyester polyol (A), 5 to 40 parts by mass of the aliphatic polyether polyol (B) and 5 to 25 parts by mass of the aromatic polyester polyol (CI) based on 100 parts by mass of the total amount of the polyol and the polyisocyanates.

7. (Currently amended) The moisture-curable polyurethane hot-melt adhesive according to claim 2-1, wherein

the adhesive is obtained by a reaction of the polyisocyanate and the polyols, which comprises 20 to 60 parts by mass of the long-chain aliphatic polyester polyol (A), 5 to 40 parts by mass of the aliphatic polyether polyol (B), 5 to 20 parts by mass of the aromatic polyester polyol (CI) and 5 to 20 parts by mass of the aromatic polyesterpolyol (CII), wherein the sum of the polyols (CI) and (CII) is in the range of 10 to 35 parts by mass, based on 100 parts by mass of the total amount of the polyol and the polyisocyanates.

8. (Previously Presented) The moisture-curable polyurethane hot-melt adhesive according to claim 1, wherein the urethane prepolymer comprises an island like phase separated structure.

9. (Original) The moisture-curable polyurethane hot-melt adhesive according to claim 1, wherein the melt viscosity at 125°C of the adhesive is in the range of 2,000 to 9,000 mPa·s.

10. **(Original)** A decorative fixture member, which is obtained by pasting a sheet or film on a substrate with the moisture-curable polyurethane hot-melt adhesive according to claim 1.

11. **(New)** A moisture-curable polyurethane hot-melt adhesive according to claim 1, wherein the initial adhesive strength as measured by a 180° tensile test is within a range of 5 to 10 N/25 mm.